CLAIMS:

1.   A curable composition comprising

(A) 100 parts by weight of an alkenyl-containing fluoropolymer comprising $-(CF(CF_3)-CF_2-O)-$ units,

(B) 20 to 40 parts by weight of an alkenyl-free, non-functional fluoropolymer comprising $-[(CF_2)_kO]-$ units wherein k is 1 to 6,

(C) a cure effective amount of an organohydrogensiloxane having at least two hydrogen atoms each attached to a silicon atom in a molecule, and

(D) a catalytic amount of a platinum group metal catalyst.

2.   The curable composition of claim 1 wherein component (A) comprises a branched polyfluorodialkenyl compound of the following general formula (1):

$$CH_2=CH-(X)_a-Rf^1-(X')_a-CH=CH_2 \hspace{2cm} (1)$$

wherein X is a divalent group represented by $-CH_2-$, $-CH_2O-$, $-CH_2OCH_2-$ or $-Y-NR^1-CO-$ wherein Y is a divalent group represented by $-CH_2-$ or


and R^1 is hydrogen or a substituted or unsubstituted monovalent hydrocarbon group,

X' is a divalent group represented by $-CH_2-$, $-OCH_2-$, $-CH_2OCH_2-$ or $-CO-NR^1-Y'-$ wherein Y' is a divalent group represented by $-CH_2-$ or


and R^1 is as defined above, "a" is independently equal to 0 or 1,

Rf^1 is a divalent group having the general formula (i):

$$-C_tF_{2t}-[OCF_2CF(CF_3)]_p-O-CF_2(CF_2)_rCF_2-O-[CF(CF_3)CF_2O]_q-C_tF_{2t}- \quad (i)$$

wherein p and q each are an integer of 1 to 150, the sum of p and q on average is 2 to 200, r is an integer of 0 to 6, and t is 2 or 3, or the general formula (ii):

$$-C_tF_{2t}-[OCF_2CF(CF_3)]_u-(OCF_2)_v-OC_tF_{2t}- \quad (ii)$$

wherein u is an integer of 1 to 200, v is an integer of 1 to 50, and t is as defined above.

3. The curable composition of claim 2 wherein component (A) further comprises a branched polyfluoromonoalkenyl compound of the following general formula (2):

$$Rf^2-(X')_a-CH=CH_2 \quad (2)$$

wherein X' and "a" are as defined above, Rf^2 is a group of the general formula (iii):

$$F-[CF(CF_3)CF_2O]_w-C_tF_{2t}- \quad (iii)$$

wherein t is as defined above, and w is an integer of 1 to 150, which is smaller than any of the sum of p+q (average) and r and the sum of u and v for Rf^1 in formula (1).

4. The curable composition of claim 2 wherein component (B) is at least one linear polyfluoro compound selected from the group consisting of compounds having the general formula (3):

$$A-O-(CF_2CF_2CF_2O)_c-A \quad (3)$$

wherein A is a group of the formula: $C_sF_{2s+1}-$ wherein s is 1 to 3, and c is an integer of 1 to 200, which is smaller than any of the sum of p+q (average) and r and the sum of u and v for Rf^1 in formula (1), and compounds having the general formula (4):

$$A-O-(CF_2O)_d(CF_2CF_2O)_e-A \quad (4)$$

wherein A is as defined above, d and e each are an integer of 1 to 200, and the sum of d and e is equal to or smaller than any of the sum of p+q (average) and r and the sum of u and v for Rf^1 in formula (1).

5

5.   An electric or electronic part encapsulated with the curable composition of any one of claim 1.